



FOAM SPECIFICATION SHEET

GRADE	COLOUR	DENSITY KG/M3	HARDNESS Newtons	USES
16/40	Yellow	16	40	Soft Backs, pillows
16/100	Apricot	16	100	Backs, budget mattresses
19/130	White	19	130	Firm Backs, overlays
25/130	Pink	25	130	Mattresses, thin backs
27/115	Green	27	115	Seats, Superior mattresses
28/70	Pink	28	70	Soft Superior backs
28/160	White	28	160	Firm seats, window seats
28/190	Lt Green	28	190	Firm Overlays
29/330	White	29	330	Packing foam
32/100	Lt Pink	32	100	Soft Superior seating
35/127	Orange	35	127	Medium Superior seating
35/160	Blue	35	160	Firm superior seating
36/200	Yellow	36	200	Firm thin seats, dining chair
BR115	Multi	115	N/A	Rebonded Foam

All Foam is made in New Zealand

Densities quoted are plus or minus 1 KG/M3

Hardness's quoted are plus or minus 10 Newtons.

Foam tested to BS4443 for Hardness.